

Centre de Recherches et d'Etudes Techniques du Tapis

# REACTION TO FIRE CLASSIFICATION REPORT N° 2013/023

According to EN 13501-1 (2007) + A1 (2009)

Notification by the French Government to the European Commission under n° NB 2401

Sponsor:

GERFLOR PROVENCE SNC

Route de Taulignan 84600 GRILLON

**FRANCE** 

Product name:

**ATTRACTION** 

Description:

Resilient floor covering in tiles (EN 649 family)

(see detailed description in paragraph 2)

Date of issue:

18/03/2013

The indicated classification does not prejudge the conformity of marketed materials with the samples submitted to the tests and under no circumstances, this document should not be considered as type approval or certification of the product in the sense of the L 115-27 article of the consumption's code of the law dated June 3<sup>rd</sup> 1994.

The reproduction of this classification report is only authorised in its integral form. It comprise 3 pages

Classification report

N° RC 2013/023

### 1. Introduction

This classification report defines the classification assigned to the above-mentioned product (s) in accordance with the procedures given in the NF EN 13501-1 standard: September 2007 & A1 (2009).

# 2. Details of classified product

## 2.1. Product standard

NF EN 14041 (2005): «Resilient, textile and laminate floor coverings - Essential characteristics.

# 2.2. Product description

PVC Resilient floor covering in tiles of 650 x 650 mm.

Tested loose laid over a 6 mm thick fibre-cement board classified  $A1_{\rm fl}$  or  $A2_{\rm fl}$  with a density (1800 ± 200) Kg/m<sup>3</sup>

Use surface: 100 % PVC.

Nominal mass per unit area: 7420 g/m<sup>2</sup>. Nominal total thickness: 5,0 mm.

### 3. Test reports and tests results in support of this classification

### 3.1. Tests reports

Name of laboratory	Name of sponsor	Test report N°	Test method
C.R.E.T.	GERFLOR PROVENCE Route de Taulignan 84600 GRILLON FRANCE	RL 2013/094-1	ISO 9239-1
		RL 2013/094 -2	NF EN ISO 11925-2

### 3.2. Tests results

		Number of tests	Results	
Test method	Product		Parameters	Compliance parameters
NF EN ISO 11925-2	ATTRACTION	6	Fs ≤ 150 mm	Compliant
Surface exposure-15 secondes			Ignition of the filter paper	Compliant

				Results
Test method	Product	Number of tests	Parameters	Continuous parameters : mean value
ISO 9239-1	A TTD A CTION	3	Critical heat flux (kW/m²)	8,3
	ATTRACTION		Smoke (% X min)	528,5

## 4. Classification and field of application

#### 4.1. Reference of classification

This classification has been carried out in accordance with EN 13501-1:2007 & A1 (2009).

#### 4.2. Classification

Fire behaviour		Smoke production
$B_{\mathrm{fl}}$	<b>**</b>	s1

Classification: B<sub>fl</sub>-s1

# 4.3. Field of application

This classification is valid for the following end use applications:

Loose laid and glued over fibre-cement A2<sub>fl</sub> or A1<sub>fl</sub> class with a density  $\geq 1350 \text{ kg/m}^3$ .

This classification is valid for the following product parameters:

A nominal mass per unit area of: 7420 g/m²

A nominal thickness of: 5,0 mm

#### 5. Limitations

This classification document does not represent type approval or certification of the product.

"The classification assigned to the product in this report is appropriate to a declaration of conformity by the manufacturer within the context of system 3 attestation of conformity and CE marking under the Construction Products Directive.

The manufacturer has made a declaration, which is held on file. This confirms that the products design requires no specific processes, procedures or stages (no addition of flame-retardants, limitation of organic content, or addition of fillers) that are aimed at enhancing the fire performance in order to obtain the classification achieved. As a consequence the manufacturer has concluded that system 3 attestation is appropriate.

The test laboratory has, therefore, played no part in sampling the product for the test, although it holds appropriate references, supplied by the manufacturer, to provide for traceability of the samples tested."

The Responsible for the Test David VANDIERDONCK

For the SARL C.R.E.T. The Technical Director Marc WELCOMME

End of the classification report